

# EXISTENCE AND TIME-DISCRETIZATION FOR THE FINITE-STRAIN SOUZA-AURICCHIO CONSTITUTIVE MODEL FOR SHAPE-MEMORY ALLOYS

SERGIO FRIGERI AND ULISSE STEFANELLI

ABSTRACT. We prove the global existence of solutions for a shape-memory alloys constitutive model at finite strains. The model has been presented in [24] and corresponds to a suitable finite-strain version of the celebrated Souza-Auricchio model for SMAs [6, 55]. We reformulate the model in purely variational fashion under the form of a rate-independent process. Existence of suitably weak (energetic) solutions to the model is obtained by passing to the limit within a constructive time-discretization procedure.

## 1. INTRODUCTION

Shape-memory alloys (SMAs) show abrupt diffusionless stress- and temperature-driven martensitic phase-changes. At the macroscopic level, the result is an amazing thermomechanical behavior. At certain (suitably high) temperature regimes SMAs are *superelastic*, namely, they completely recover comparably large deformations during mechanical loading-unloading cycles. At lower temperatures, severely deformed specimens regain their original shape after a thermal treatment. This is the so-called *shape-memory effect* [26].

The specific thermomechanical behavior of SMAs is not present (at least to a comparable extent) in materials traditionally used in engineering and is at the basis of a variety of innovative applications to aeronautical, structural, earthquake, and biomedical technologies [19, 20], just to mention a few hot topics. This fact motivated an intense research toward a comprehensive and effective description of the complex thermomechanical behavior of SMAs. The relevant engineering literature on SMAs modeling is vast and a whole menagerie of models have been advanced having ambitions for different ranges of applicability (from lab single-crystal experiments to commercially exploitable tools) and different abilities to fit particular experiments and to explain microstructures, stress/strain relations, or hysteresis. In the macroscopic-phenomenological setting, the reader shall be minimally referred to [12, 25, 28, 31, 33, 35, 51, 52, 53, 57] and to the survey [54].

We are here concerned with a phenomenological, internal-variable-type model for polycrystalline shape-memory bodies originally advanced in the *small-strain regime* by SOUZA, MAMIYA, & ZOUAIN [55] and combined with finite elements by AURICCHIO & PETRINI [6, 7, 8], hence referred to as *Souza-Auricchio* in the following. This model describes very efficiently both the superelastic and the shape-memory behavior. Moreover, it shows a remarkable robustness with respect to parameters and discretizations despite its *simplicity*: the constitutive behavior of the material is determined by 8 easily-fitted material parameters [5, 11] (note that linearized thermo-plasticity with linear hardening already requires 5 material parameters). The Souza-Auricchio model admits a sound mathematical treatment. It has been analyzed from the viewpoint of existence and approximation of solutions of the isothermal three-dimensional quasi-static evolution problem in [5] and convergence rates for space-time discretizations are discussed

---

2010 *Mathematics Subject Classification.* 74C15; 74N30.

*Key words and phrases.* Shape-memory alloys; finite-strain; Phase transformations in Solids; Rate-independence; Existence; Time-discretization.

in [46, 47]. Results in the non-isothermal case have also been obtained [22, 29, 30, 48, 45]. Moreover, extensions of the original model to residual plasticity [9, 10, 21], more realistic non-symmetric behaviors and transformation-dependent material parameters [11], and the ferromagnetic shape-memory effect [3, 4, 14, 15, 56] are also available.

This note is focused on the *finite-strain* version of the Souza-Auricchio model advanced by EVANGELISTA, ET AL. [23, 24] and considered also in ARGHAVANI ET AL. [1]. Note that shape-memory devices are generally engineered in order to exploit martensitic-transformation-induced inelastic strains up to 8%. This sets clearly beyond the possible reach of linearized elasticity theory calling for a finite-strain analysis instead. In [24] the authors propose a finite-strain choice for the free energy of the material, a specific flow rule for the internal variable, and formally verify the recovery of the small-strain Souza-Auricchio model upon strain linearization. Moreover, some comments on algorithmical aspects of a possible fully-implicit time-discretization of the constitutive relation and the integration of the latter in some finite elements test is reported.

A first issue of this paper is that of reformulating the finite-strain model of [24] in a purely variational fashion. This complements the analysis of [24] where material relations (in particular, the flow rule) are presented via the classical complementary formalism. The variational reformulation of the model bears a clear mathematical advantage as it provides the possibility of recasting the constitutive relation in terms of symmetric right Cauchy-Green tensors only.

Secondly, this novel variational reformulation of the model allows us to settle the material constitutive problem within the now quite developed theory of rate-independent processes. This in turn provides the possibility of proving the convergence of time discretizations of the material constitutive relation. In particular, the material constitutive relation is proved to admit a suitably defined *energetic solution* [49]. Note that no convergence nor existence proof is reported in the former [24].

We directly develop our analysis in the non-isothermal regime, by however letting the temperature of the body being given a-priori. This assumption seems justified in case of a shape-memory body which is thin in at least one direction and for slowly varying loads. In this case, one could assume that the heat which is mechanically produced within the sample gets immediately transferred to the surrounding heat bath. This perspective is followed in [22, 48, 45] in the small-strain regime. On the contrary, a fully thermomechanically coupled problem for the small-strain model is solved in one spatial dimension in [29, 30]. Note that the smoothness on the given temperature here assumed is weaker than the corresponding one from [48, 45] exactly in the same spirit as in [22]. It would indeed be interesting to consider the fully thermomechanically coupled problem, i.e., coupling the constitutive relation with three-dimensional quasi-static mechanics and temperature evolution. On the other hand, this seems presently out of reach, even in the comparably simpler small-strain case [29, 30].

Before moving on, let us briefly review the literature on phenomenological SMA constitutive modeling at finite-strains. A first reference in this direction is AURICCHIO & TAYLOR [13], where a pseudo-elastic constitutive model is presented. The finite-strain model from [13] reduces to the so-called  $R_L$  model by RANIECKI & LEXCELLENT [52] upon strain linearization. Other extensions of the  $R_L$  model to finite strains are to be found in ZIOLKOWSKI [58], where thermo-mechanical coupling effects are also considered, and MÜLLER & BRUHNS [50], where an additive decomposition of the deformation gradient is performed. Finite-strain models based on multiplicative decomposition instead are in HELM & HAUPT [28] and REESE & CHRIST [18, 53]. Eventually, the small-strain model by PANICO & BRINSON [32] has been extended to the finite-deformations realm in ARGHAVANI ET AL. [2].

To our knowledge, the mathematical treatment here presented is unprecedented with respect to the above-reviewed literature as none of the mentioned finite-strain constitutive SMA models has already

obtained consideration from the viewpoint of existence of solutions nor convergence proofs of time discretizations. On the other hand, we shall mention the mathematical results in MAINICK & MIELKE [40] and MIELKE ET AL. [41, 42, 43, 44] where existence of solutions for quasistatic incremental problems and *energetic* evolutions in finite-strain elastoplasticity (including higher order gradient terms though) are discussed. Note that here we limit ourselves in considering the finite-dimensional situation of the constitutive relation. In particular, we shall tackle the full PDE quasistatic evolution problem elsewhere.

The paper is organized as follows. In Section 2 we recall the basics of the model from [24] and comment on dissipativity whereas Section 3 is devoted to the *variational reformulation* of the model. Then, Section 4 brings to the convergence proof of time-incremental approximations and, in particular, to the existence of energetic solutions.

## 2. THE MODEL

The aim of this section is that of recalling the model from [24]. We limit ourselves to mention the essential modeling features and notation. The reader is instead referred to [24] for additional details and comments as well as some numerical evidence of the performance of the model.

**2.1. Tensors.** We shall use bold capital letters for 2-tensors in  $\mathbb{R}^{d \times d}$  ( $d = 2, 3$ ) and double capitals (e.g.,  $\mathbb{T}$ ) for 4-tensors. Let  $\mathbb{R}^{d \times d}$  be the space of 2-tensors endowed with the natural scalar product  $\mathbf{A}:\mathbf{B} \doteq A_{ij}B_{ij}$  (summation convention) and the corresponding norm  $|\mathbf{A}|^2 \doteq \mathbf{A}:\mathbf{A}$  for all  $\mathbf{A}, \mathbf{B} \in \mathbb{R}^{d \times d}$ . The symbol  $\mathbb{R}_{\text{sym}}^{d \times d}$  denotes the subspace of symmetric tensors. The space  $\mathbb{R}_{\text{sym}}^{d \times d}$  is orthogonally decomposed as  $\mathbb{R}_{\text{sym}}^{d \times d} = \mathbb{R}_{\text{dev}}^{d \times d} \oplus \mathbb{R}\mathbf{1}$ , where  $\mathbb{R}\mathbf{1}$  is the subspace spanned by the identity 2-tensor  $\mathbf{1}$  and  $\mathbb{R}_{\text{dev}}^{d \times d}$  is the subspace of symmetric and deviatoric tensors. In particular, for all  $\mathbf{A} \in \mathbb{R}_{\text{sym}}^{d \times d}$ , we let  $\text{tr } \mathbf{A} \doteq \mathbf{A}:\mathbf{1}$  and  $\text{dev } \mathbf{A} \doteq \mathbf{A} - (\text{tr } \mathbf{A})\mathbf{1}/d$  so that  $\mathbf{A} = \text{dev } \mathbf{A} + (\text{tr } \mathbf{A})\mathbf{1}/d$ . On the other hand, the identity 4-tensor  $\mathbb{I}$  is given by  $\mathbb{I}_{ijkl} \doteq \delta_{il}\delta_{jk}$  and we have  $\mathbb{I}:\mathbf{A} = \mathbf{A}:\mathbb{I} = \mathbf{A}$ . We shall use the classical notation

$$\begin{aligned} \text{GL}_+(d) &\doteq \{\mathbf{A} \in \mathbb{R}^{d \times d} \mid \det \mathbf{A} > 0\}, \\ \text{SL}(d) &\doteq \{\mathbf{A} \in \mathbb{R}^{d \times d} \mid \det \mathbf{A} = 1\}, \quad \text{SO}(d) \doteq \{\mathbf{A} \in \text{SL}(d) \mid \mathbf{A}^\top \mathbf{A} = \mathbf{A}\mathbf{A}^\top = \mathbf{1}_2\} \end{aligned}$$

where  $A^\top$  is the transpose of the tensor  $A \in \mathbb{R}^{d \times d}$ .

The 2-tensors  $\mathbb{T}:\mathbf{B}$  and  $\mathbf{B}:\mathbb{T}$  are classically defined by  $(\mathbf{B}:\mathbb{T})_{ik} \doteq B_{jl}T_{jlik}$  and  $(\mathbb{T}:\mathbf{B})_{ik} \doteq T_{iklj}B_{lj}$ , respectively. Given the smooth function  $\mathbf{B} \mapsto \mathbf{A}(\mathbf{B})$  we shall denote by  $\partial_{\mathbf{B}}\mathbf{A}$  the 4-tensor defined by  $(\partial_{\mathbf{B}}\mathbf{A})_{ikjl} \doteq \partial_{B_{j\ell}}A_{ik}$  or, equivalently,

$$\partial_{\mathbf{B}}\mathbf{A}:\mathbf{C} \doteq \left. \frac{d}{d\alpha} \mathbf{A}(\mathbf{B} + \alpha\mathbf{C}) \right|_{\alpha=0} \quad \forall \mathbf{C} \in \mathbb{R}^{d \times d}.$$

In particular, we have that

$$(\partial_{\mathbf{B}}\mathbf{A}:\mathbf{C})_{ik} = \partial_{B_{j\ell}}A_{ik}C_{j\ell}, \quad (\mathbf{C}:\partial_{\mathbf{B}}\mathbf{A})_{ik} = C_{j\ell}\partial_{B_{ik}}A_{j\ell}$$

for all  $\mathbf{C} \in \mathbb{R}^{d \times d}$ . Note that the associative property  $(\mathbf{C}:\partial_{\mathbf{B}}\mathbf{A}):\mathbf{D} = \mathbf{C}:(\partial_{\mathbf{B}}\mathbf{A}:\mathbf{D})$  holds for every  $\mathbf{C}, \mathbf{D} \in \mathbb{R}^{d \times d}$ , and we can write  $\mathbf{C}:\partial_{\mathbf{B}}\mathbf{A}:\mathbf{D}$  without ambiguity. Note also that  $\partial_{\mathbf{A}}\mathbf{A} = \mathbb{I}$ .

The 4-tensor  $\mathbb{T}_1:\mathbb{T}_2$  is defined by  $(\mathbb{T}_1:\mathbb{T}_2)_{ijkl} \doteq (\mathbb{T}_1)_{ijmn}(\mathbb{T}_2)_{mnkl}$ . In particular, if  $\mathbf{A}$  is a function of  $\mathbf{B}$  and  $\mathbf{C}$  is a function of  $\mathbf{D}$  (all 2-tensors), we have

$$(\partial_{\mathbf{B}}\mathbf{A}:\partial_{\mathbf{D}}\mathbf{C})_{ikjl} = \partial_{B_{mn}}A_{ik}\partial_{D_{j\ell}}C_{mn}.$$

We have that  $\mathbf{A}:(\mathbb{T}_1:\mathbb{T}_2) = (\mathbf{A}:\mathbb{T}_1):\mathbb{T}_2$  and  $(\mathbb{T}_1:\mathbb{T}_2):\mathbf{B} = \mathbb{T}_1:(\mathbb{T}_2:\mathbf{B})$  for every  $\mathbf{A}, \mathbf{B} \in \mathbb{R}^{d \times d}$  so that brackets can be omitted. Finally, the product derivative formulas

$$\partial_{\mathbf{A}}(\mathbf{B}\mathbf{C}):\mathbf{D} = (\partial_{\mathbf{A}}\mathbf{B}:\mathbf{D})\mathbf{C} + \mathbf{B}(\partial_{\mathbf{A}}\mathbf{C}:\mathbf{D}) \quad (2.1)$$

$$\mathbf{B}:\partial_{\mathbf{A}}(\mathbf{C}\mathbf{D}) = \mathbf{B}\mathbf{D}^\top:\partial_{\mathbf{A}}\mathbf{C} + \mathbf{C}^\top\mathbf{B}:\partial_{\mathbf{A}}\mathbf{D} \quad (2.2)$$

will turn out to be useful in the following.

**2.2. Deformation gradient.** Let  $\varphi : \Omega \rightarrow \mathbb{R}^d$  denote the deformation of the SMA sample from the reference configuration  $\Omega \subset \mathbb{R}^d$ . We shall classically decompose the deformation gradient  $\mathbf{D}\varphi$  as [34]

$$\mathbf{D}\varphi = \mathbf{F} = \mathbf{F}_{\text{el}}\mathbf{F}_{\text{tr}}$$

where  $\mathbf{F}_{\text{el}}$  stands for the *elastic* deformation gradient whereas  $\mathbf{F}_{\text{tr}}$  denotes the inelastic (or *transformation*) part and is constrained to belong to  $\text{SL}(d)$  in order to ensure the inelastic deformation to be volume preserving.

In order to formulate the model, we will rely on the *right Cauchy-Green* deformation tensor

$$\mathbf{C} \doteq \mathbf{F}^\top \mathbf{F}$$

and the corresponding elastic and inelastic analogues

$$\mathbf{C}_{\text{el}} \doteq \mathbf{F}_{\text{el}}^\top \mathbf{F}_{\text{el}}, \quad \mathbf{C}_{\text{tr}} \doteq \mathbf{F}_{\text{tr}}^\top \mathbf{F}_{\text{tr}}.$$

In particular, one shall note that  $\mathbf{C}_{\text{tr}} \in \text{SL}_{\text{sym}}(d) \doteq \text{SL}(d) \cap \mathbb{R}_{\text{sym}}^{d \times d}$ .

**2.3. Free energy.** The free energy of the body is assumed to be decomposed as

$$\psi \doteq \psi_{\text{el}}(\mathbf{C}_{\text{el}}) + \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta). \quad (2.3)$$

Here,  $\theta$  denotes the absolute temperature of the sample,  $\psi_{\text{el}}$  is the *elastic part* of the free energy whereas  $\psi_{\text{tr}}$  stands for the *inelastic part*.

As for the elastic part of the energy, we shall simply assume it to be smooth far from the set where  $\det \mathbf{F} = \det \mathbf{F}_{\text{el}} \leq 0$ , frame indifferent, and isotropic. In particular,  $\psi_{\text{el}}$  is derived from an elastic potential  $W \in C^1(\text{GL}_+(d))$  via  $\psi_{\text{el}}(\mathbf{C}_{\text{el}}) \doteq W(\mathbf{F}_{\text{el}})$  with  $W : \mathbb{R}^{d \times d} \rightarrow [0, \infty]$  such that

$$W(\mathbf{R}\mathbf{F}_{\text{el}}) = W(\mathbf{F}_{\text{el}}) \quad \forall \mathbf{R} \in \text{SO}(d), \mathbf{F}_{\text{el}} \in \mathbb{R}^{d \times d}, \quad (2.4)$$

$$W(\mathbf{F}_{\text{el}}\widehat{\mathbf{R}}) = W(\mathbf{F}_{\text{el}}) \quad \forall \widehat{\mathbf{R}} \in \text{SO}(d), \mathbf{F}_{\text{el}} \in \mathbb{R}^{d \times d}, \quad (2.5)$$

$$|\partial_{\mathbf{F}_{\text{el}}} W(\mathbf{F}_{\text{el}})\mathbf{F}_{\text{el}}^\top| \leq c_0(W(\mathbf{F}_{\text{el}}) + 1). \quad (2.6)$$

The above assumptions are nothing but frame-indifference (2.4), isotropy (2.5), and the controllability of the Kirchhoff tensor in terms of the energy (2.6). In particular, they are completely compatible with the standard polyconvexity frame. Note that the functional  $W$  can be additionally asked to fulfill

$$W(\mathbf{F}_{\text{el}}) \rightarrow \infty \quad \text{for} \quad \det \mathbf{F}_{\text{el}} \rightarrow 0^+.$$

The specific form for the inelastic energy  $\psi_{\text{tr}}$  is chosen as

$$\psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta) \doteq b(\theta - \theta_M)^+ |\mathbf{E}_{\text{tr}}| + \frac{h}{2} |\mathbf{E}_{\text{tr}}|^2 + I_{\epsilon_L}(\mathbf{E}_{\text{tr}}) \quad (2.7)$$

where  $\mathbf{E}_{\text{tr}}$  is the inelastic *Green-St. Venant* tensor

$$\mathbf{E}_{\text{tr}} \doteq \frac{1}{2}(\mathbf{C}_{\text{tr}} - \mathbf{1}_2),$$

$b > 0$ ,  $\theta_M > 0$  is the critical martensite-austenite transition temperature at zero stress,  $h > 0$  is a kinematic hardening modulus, and  $I_{\epsilon_L}$  is the indicator function of the set  $\{\mathbf{E}_{\text{tr}} \in \mathbb{R}^{d \times d} \mid |\mathbf{E}_{\text{tr}}| \leq \epsilon_L\}$  with

$\epsilon_L > 0$  representing a measure of the maximal strain obtainable via martensitic variants reorientation. In particular, we have that

$$I_{\epsilon_L}(\mathbf{E}_{\text{tr}}) \doteq \begin{cases} 0 & \text{if } |\mathbf{E}_{\text{tr}}| \leq \epsilon_L \\ \infty & \text{else.} \end{cases}$$

We shall stick to the specific form (2.7) for the inelastic energy for the sake of reference with the original model in [24]. Let us however mention that the mathematical considerations developed hereafter apply to a much broader class of energies, possibly including kinematic-hardening finite-strain plasticity. Although close from the mathematical viewpoint, the present SMA model and kinematic-hardening plasticity differ under two respects. A first difference is the occurrence of the constraint  $|\mathbf{E}_{\text{tr}}| \leq \epsilon_L$  on the inelastic response of the material. In particular, all energetic solutions fulfill this constraint pointwise everywhere in time as a consequence of the finiteness of the energy. The second difference relies on the linear growth in  $\mathbf{C}_{\text{tr}}$  of the thermo-mechanical coupling term  $b(\theta - \theta_M)^+ |\mathbf{E}_{\text{tr}}|$  in the inelastic energy, see (2.7).

Throughout this work we shall assume the absolute temperature  $t \mapsto \theta(t)$  to be given. This in particular motivates the absence of the classical purely caloric term  $c_V \theta(1 - \ln \theta)$  in the expression of the free energy (2.3) ( $c_V$  being the specific heat). Note that, even by including such term into the free energy, the model is not directly suited for describing fully coupled thermomechanical evolutions as the choice (2.7) (which is motivated in the isothermal frame) would prescribe the non-monotone temperature-entropy relation

$$s \doteq -\partial_\theta \psi = c_V \ln \theta - bH(\theta - \theta_M) |\mathbf{E}_{\text{tr}}|$$

where  $H$  stands for the classical Heaviside function. Further details on this issue are to be found in [29, 30].

**2.4. Clausius-Duhem inequality.** Let us complement the analysis of [24] and provide some detail in the direction of the Clausius-Duhem inequality for the body. In particular, this reduces to check that, at least for smooth evolutions,

$$-\dot{\psi} - s\dot{\theta} + \mathbf{S} : \frac{1}{2} \dot{\mathbf{C}} - \mathbf{q} \cdot \frac{\nabla \theta}{\theta} \geq 0 \quad (2.8)$$

where  $s$  is the *entropy*,  $\mathbf{S}$  is the *second Piola-Kirchhoff stress tensor*, and  $\mathbf{q}$  is the *heat flux*. With the aid of (2.3), we manipulate the term  $-\dot{\psi} + \mathbf{S} : \dot{\mathbf{C}}/2$  in the above left-hand side as follows

$$\begin{aligned} -\dot{\psi} + \mathbf{S} : \frac{1}{2} \dot{\mathbf{C}} &= -\frac{d}{dt} (\psi_{\text{el}}(\mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1}) + \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta)) + \mathbf{S} : \frac{1}{2} \dot{\mathbf{C}} \\ &= -\partial_\theta \psi \dot{\theta} - \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : (-\mathbf{F}_{\text{tr}}^{-\top} \dot{\mathbf{F}}_{\text{tr}}^\top \mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1} + \mathbf{F}_{\text{tr}}^{-\top} \dot{\mathbf{C}} \mathbf{F}_{\text{tr}}^{-1} - \mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1} \dot{\mathbf{F}}_{\text{tr}} \mathbf{F}_{\text{tr}}^{-1}) \\ &\quad - \partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{tr}} : \dot{\mathbf{C}}_{\text{tr}} + \mathbf{S} : \frac{1}{2} \dot{\mathbf{C}} \\ &= -\partial_\theta \psi \dot{\theta} + \left( \mathbf{S} - 2\mathbf{F}_{\text{tr}}^{-1} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} \mathbf{F}_{\text{tr}}^{-\top} \right) : \frac{1}{2} \dot{\mathbf{C}} \\ &\quad + \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} \mathbf{C}_{\text{el}} : \mathbf{F}_{\text{tr}}^{-\top} \dot{\mathbf{F}}_{\text{tr}}^\top + \mathbf{C}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : \dot{\mathbf{F}}_{\text{tr}} \mathbf{F}_{\text{tr}}^{-1} - \partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{tr}} : \dot{\mathbf{C}}_{\text{tr}} \\ &= -\partial_\theta \psi \dot{\theta} + \left( \mathbf{S} - 2\mathbf{F}_{\text{tr}}^{-1} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} \mathbf{F}_{\text{tr}}^{-\top} \right) : \frac{1}{2} \dot{\mathbf{C}} \\ &\quad + \left( 2\mathbf{F}_{\text{tr}}^{-1} \mathbf{C}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} \mathbf{F}_{\text{tr}}^{-\top} - 2\partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{tr}} \right) : \frac{1}{2} \dot{\mathbf{C}}_{\text{tr}} \end{aligned} \quad (2.9)$$

where we used the coaxiality of  $\mathbf{C}_{\text{el}}$  and  $\partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}}$  (which in turn follows from isotropy (2.5)), the identity  $\dot{\mathbf{C}}_{\text{tr}} = \dot{\mathbf{F}}_{\text{tr}}^\top \mathbf{F}_{\text{tr}} + \mathbf{F}_{\text{tr}}^\top \dot{\mathbf{F}}_{\text{tr}}$ , and the short-hand notation  $\partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} = \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}}(\mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1})$  and  $\partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{tr}} = \partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta)$  (here and in the following). We shall systematically make use of the symbol  $\partial$  for the

*subdifferential* of a convex function [16]. In particular, given any  $\phi : \mathbb{R}^{d \times d} \rightarrow (-\infty, \infty]$  convex, we denote its *subdifferential*  $\partial\phi$  as

$$\mathbf{B} \in \partial\phi(\mathbf{A}) \iff \phi(\mathbf{A}) < \infty \text{ and } \mathbf{B} : (\mathbf{T} - \mathbf{A}) \leq \phi(\mathbf{T}) - \phi(\mathbf{A}) \quad \forall \mathbf{T} \in \mathbb{R}^{d \times d}.$$

Note incidentally that, as  $\psi_{\text{tr}}$  is non-smooth, the symbol  $\partial_{\mathbf{C}_{\text{tr}}}\psi_{\text{tr}}$  represents a *selection* in the convex set  $\partial_{\mathbf{C}_{\text{tr}}}\psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta)$ .

**2.5. Constitutive relations and flow rule.** We let the second Piola-Kirchhoff stress tensor  $\mathbf{S}$  be given by

$$\mathbf{S} \doteq 2\mathbf{F}_{\text{tr}}^{-1}\partial_{\mathbf{C}_{\text{el}}}\psi_{\text{el}}\mathbf{F}_{\text{tr}}^{-\top}$$

and define

$$\mathbf{T} \doteq \mathbf{F}_{\text{tr}}^{-1}\mathbf{M}\mathbf{F}_{\text{tr}}^{-\top} - \mathbf{A} \tag{2.10}$$

where

$$\mathbf{M} \doteq 2\mathbf{C}_{\text{el}}\partial_{\mathbf{C}_{\text{el}}}\psi_{\text{el}}, \quad \mathbf{A} \doteq 2\partial_{\mathbf{C}_{\text{tr}}}\psi_{\text{tr}} \tag{2.11}$$

are the so-called *Mandel stress* and *back stress*, respectively [53]. Owing to the computation in (2.9), the tensor  $\mathbf{T}$  is the thermodynamic force associated with the internal variable  $\mathbf{C}_{\text{tr}}$  for we have that

$$2\mathbf{F}_{\text{tr}}^{-1}\mathbf{C}_{\text{el}}\partial_{\mathbf{C}_{\text{el}}}\psi_{\text{el}}\mathbf{F}_{\text{tr}}^{-\top} - 2\partial_{\mathbf{C}_{\text{tr}}}\psi_{\text{tr}} = \mathbf{F}_{\text{tr}}^{-1}\mathbf{M}\mathbf{F}_{\text{tr}}^{-\top} - \mathbf{A} = \mathbf{T}.$$

Let us stress that both the Mandel stress  $\mathbf{M}$  and the back stress  $\mathbf{A}$  are symmetric ( $\mathbf{M}$  by the coaxiality of  $\mathbf{C}_{\text{el}}$  and  $\partial_{\mathbf{C}_{\text{el}}}\psi_{\text{el}}$  and  $\mathbf{A}$  by the current choice of  $\psi_{\text{tr}}$ ) so that  $\mathbf{T} = \mathbf{F}_{\text{tr}}^{-1}\mathbf{M}\mathbf{F}_{\text{tr}}^{-\top} - \mathbf{A}$  is symmetric as well.

The dissipative evolution of the material is prescribed via the associative *flow rule*

$$\dot{\mathbf{C}}_{\text{tr}} = \dot{\zeta}\partial_{\mathbf{T}}f(\mathbf{F}_{\text{tr}}, \mathbf{T}). \tag{2.12}$$

for some *yield function*  $f : \mathbb{R}^{d \times d} \times \mathbb{R}_{\text{sym}}^{d \times d} \rightarrow \mathbb{R}$ , such that for all  $\mathbf{F}_{\text{tr}} \in \mathbb{R}^{d \times d}$  the function  $f(\mathbf{F}_{\text{tr}}, \cdot)$  is convex and positively 1-homogeneous ( $f(\mathbf{F}_{\text{tr}}, \lambda\mathbf{T}) = \lambda f(\mathbf{F}_{\text{tr}}, \mathbf{T})$  for all  $\lambda \geq 0$ ), along with the classical Kuhn-Tucker complementarity conditions

$$\dot{\zeta} \geq 0, \quad f \leq 0, \quad \dot{\zeta}f = 0. \tag{2.13}$$

Following [23, 24], we choose the yield function  $f$  as

$$f(\mathbf{F}_{\text{tr}}, \mathbf{T}) = |\text{dev}(\mathbf{F}_{\text{tr}}\mathbf{T}\mathbf{F}_{\text{tr}}^{\top})| - r \tag{2.14}$$

where  $r > 0$  plays the role of a given *yield stress*.

Along with this choice, the flow rule (2.12)-(2.13) reads

$$\dot{\mathbf{C}}_{\text{tr}} \in \begin{cases} \dot{\zeta}\mathbf{F}_{\text{tr}}^{\top} \frac{\text{dev}(\mathbf{F}_{\text{tr}}\mathbf{T}\mathbf{F}_{\text{tr}}^{\top})}{|\text{dev}(\mathbf{F}_{\text{tr}}\mathbf{T}\mathbf{F}_{\text{tr}}^{\top})|} \mathbf{F}_{\text{tr}} & \text{if } \text{dev}(\mathbf{F}_{\text{tr}}\mathbf{T}\mathbf{F}_{\text{tr}}^{\top}) \neq 0, \\ \dot{\zeta}\mathbf{F}_{\text{tr}}^{\top} \{\mathbf{B} \in \mathbb{R}_{\text{dev}}^{d \times d} \cap \mathbb{R}_{\text{sym}}^{d \times d} : |\mathbf{B}| \leq 1\} \mathbf{F}_{\text{tr}} & \text{if } \text{dev}(\mathbf{F}_{\text{tr}}\mathbf{T}\mathbf{F}_{\text{tr}}^{\top}) = 0. \end{cases} \tag{2.15}$$

Note in particular that  $\dot{\mathbf{C}}_{\text{tr}} \in \mathbb{R}_{\text{sym}}^{d \times d}$ . Hence, all evolutions  $t \mapsto \mathbf{C}_{\text{tr}}(t)$  fulfilling the latter flow rule and starting from a symmetric initial datum stay in  $\mathbb{R}_{\text{sym}}^{d \times d}$  for all times.

**2.6. Dissipativity.** The above choices for constitutive relations and flow rule entail the validity of the Clausius-Duhem inequality (2.8), at least for smooth evolutions. Indeed, we may equivalently rewrite (2.12)-(2.13) or (2.15) as

$$\mathbf{T} \in \partial_{\dot{\mathbf{C}}_{\text{tr}}} R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \quad (2.16)$$

where  $R(\mathbf{F}_{\text{tr}}, \cdot) \doteq f^*(\mathbf{F}_{\text{tr}}, \cdot)$  is the classical Legendre conjugate of  $f(\mathbf{F}_{\text{tr}}, \cdot)$ . Namely, by the 1-homogeneity of  $f$ , the function  $R(\mathbf{F}_{\text{tr}}, \cdot)$  is the *support function* of the convex set  $\{\mathbf{T} \in \mathbb{R}_{\text{sym}}^{d \times d} \mid f(\mathbf{F}_{\text{tr}}, \mathbf{T}) \leq 0\}$ . In particular,

$$R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \doteq \sup\{\mathbf{T} : \dot{\mathbf{C}}_{\text{tr}} \mid f(\mathbf{F}_{\text{tr}}, \mathbf{T}) \leq 0\}.$$

Namely,  $R(\mathbf{F}_{\text{tr}}, \mathbf{0}) = 0$  and we have that, for all  $(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}})$  with  $R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) < \infty$ ,

$$\partial_{\dot{\mathbf{C}}_{\text{tr}}} R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \doteq \left\{ \mathbf{T} \in \mathbb{R}_{\text{sym}}^{d \times d} \mid \mathbf{T} : (\mathbf{B} - \dot{\mathbf{C}}_{\text{tr}}) \leq R(\mathbf{F}_{\text{tr}}, \mathbf{B}) - R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \quad \forall \mathbf{B} \in \mathbb{R}^{d \times d} \right\}.$$

Since the right-hand side of (2.9) equals  $s\dot{\theta} + \mathbf{T} : \dot{\mathbf{C}}_{\text{tr}}/2$  by definition of the entropy  $s \doteq -\partial_{\theta}\psi$  and we have

$$\mathbf{T} : \dot{\mathbf{C}}_{\text{tr}} \stackrel{(2.16)}{\geq} R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) - R(\mathbf{F}_{\text{tr}}, \mathbf{0}) = R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \geq 0,$$

by choosing the classical *Fourier* flux  $\mathbf{q} \doteq -\kappa \nabla \theta$ ,  $\kappa > 0$  we have that

$$-\dot{\psi} - s\dot{\theta} + \mathbf{S} : \frac{1}{2}\dot{\mathbf{C}} - \mathbf{q} \cdot \frac{\nabla \theta}{\theta} \geq \frac{1}{2}R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) + \kappa \nabla \theta \cdot \frac{\nabla \theta}{\theta} \geq 0.$$

In particular, the Clausius-Duhem inequality holds true.

### 3. VARIATIONAL REFORMULATION

As already remarked, one of the main issues of this paper is that of reformulating the constitutive problem in a purely variational fashion. This yields a clear advantage with respect to the original formulation of [23, 24]. In particular, this variational setting allows us to prove the convergence of the time-discretization scheme. Moreover, we shall be using the variables  $\theta, \mathbf{C}$  (given) and  $\mathbf{C}_{\text{tr}}$  (unknown) only and the model turns out to be not directly depending on  $\mathbf{F}_{\text{tr}}$ . This possibility is indeed the effect of the overall isotropy and frame-indifference assumptions and, although not new in the setting of finite-strain plasticity, it was not yet pointed out in connection with shape-memory alloys.

The first step in the direction of reformulating variationally the model consists in avoiding the use of the tensor  $\mathbf{C}_{\text{el}}$  in the definition of the free energy  $\psi$  (2.3). By recalling that

$$\mathbf{F}_{\text{tr}} = \mathbf{R}\mathbf{C}_{\text{tr}}^{1/2} = \mathbf{C}_{\text{tr}}^{1/2}\widehat{\mathbf{R}} \quad \text{for some } \mathbf{R}, \widehat{\mathbf{R}} \in \text{SO}(d) \quad (3.1)$$

we have that

$$\psi_{\text{el}}(\mathbf{C}_{\text{el}}) = \psi_{\text{el}}(\mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1}) = \psi_{\text{el}}(\mathbf{R}^{-\top} \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{R}^{-1}) = \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2}). \quad (3.2)$$

The last equality above is a consequence of (2.4)-(2.5). Indeed, let for brevity  $\mathbf{S} = \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2} = \mathbf{O}^{\top} \mathbf{D} \mathbf{O}$  with  $\mathbf{O} \in \text{SO}(d)$  and  $\mathbf{D}$  diagonal and positive definite. Hence

$$\psi_{\text{el}}(\mathbf{R}^{-\top} \mathbf{S} \mathbf{R}^{-1}) = \psi_{\text{el}}(\mathbf{R}^{-\top} \mathbf{O}^{\top} \mathbf{D} \mathbf{O} \mathbf{R}^{-1}) = W(\mathbf{R}^{-\top} \mathbf{O}^{\top} \mathbf{D}^{1/2} \mathbf{O} \mathbf{R}^{-1}) \stackrel{(2.4)+(2.5)}{=} W(\mathbf{O}^{\top} \mathbf{D}^{1/2} \mathbf{O}) = \psi_{\text{el}}(\mathbf{S})$$

whence (3.2) follows. Let us now define

$$\widehat{\psi}(\mathbf{C}, \mathbf{C}_{\text{tr}}, \theta) \doteq \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2}) + \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta).$$

We compute  $R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}})$  from the specific form of  $f(\mathbf{F}_{\text{tr}}, \mathbf{T})$  in (2.14) as

$$\begin{aligned} R(\mathbf{F}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) &= \sup \left\{ \mathbf{T} : \dot{\mathbf{C}}_{\text{tr}} \mid \mathbf{T} \in \mathbb{R}_{\text{sym}}^{d \times d}, |\text{dev}(\mathbf{F}_{\text{tr}} \mathbf{T} \mathbf{F}_{\text{tr}}^\top)| \leq r \right\} \\ &= \sup \left\{ \mathbf{T} : \dot{\mathbf{C}}_{\text{tr}} \mid \mathbf{T} \in \mathbb{R}_{\text{sym}}^{d \times d}, |\text{dev}(\mathbf{C}_{\text{tr}}^{1/2} \mathbf{T} \mathbf{C}_{\text{tr}}^{1/2})| \leq r \right\} \\ &= \sup \left\{ \mathbf{B} : \mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}_{\text{tr}} \mathbf{C}_{\text{tr}}^{-1/2} \mid \mathbf{B} \in \mathbb{R}_{\text{sym}}^{d \times d}, |\text{dev} \mathbf{B}| \leq r \right\} \\ &= \begin{cases} r |\text{dev}(\mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}_{\text{tr}} \mathbf{C}_{\text{tr}}^{-1/2})| & \text{if } \text{tr}(\mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}_{\text{tr}} \mathbf{C}_{\text{tr}}^{-1/2}) = 0 \\ \infty & \text{else.} \end{cases} \\ &= \begin{cases} r |\mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}_{\text{tr}} \mathbf{C}_{\text{tr}}^{-1/2}| & \text{if } \text{tr}(\mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}_{\text{tr}} \mathbf{C}_{\text{tr}}^{-1/2}) = 0 \\ \infty & \text{else.} \end{cases} \end{aligned}$$

Hence, one defines the *dissipation*  $\widehat{R} : \mathbb{R}_{\text{sym}}^{d \times d} \times \mathbb{R}_{\text{sym}}^{d \times d} \rightarrow [0, \infty]$  as (the meaning of the factor 1/2 will become clear in the proof of Theorem 3.1 below)

$$\widehat{R}(\mathbf{C}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \doteq \begin{cases} \frac{r}{2} |\mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}_{\text{tr}} \mathbf{C}_{\text{tr}}^{-1/2}| & \text{if } \text{tr}(\mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}_{\text{tr}} \mathbf{C}_{\text{tr}}^{-1/2}) = 0 \\ \infty & \text{else.} \end{cases}$$

The core of this section resides in the following result where we prove that one can rewrite the constitutive material relation from (2.10)-(2.13) for the internal variable  $\mathbf{C}_{\text{tr}}$  in terms of  $\widehat{R}$  and  $\widehat{\psi}$  only.

**Theorem 3.1** (Constitutive relation). *The constitutive material relation from (2.10)-(2.13) can be equivalently restated as*

$$\partial_{\dot{\mathbf{C}}_{\text{tr}}} \widehat{R}(\mathbf{C}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) + \partial_{\mathbf{C}_{\text{tr}}} \widehat{\psi}(\mathbf{C}, \mathbf{C}_{\text{tr}}, \theta) \ni \mathbf{0}. \quad (3.3)$$

*Proof.* Indeed, relations (2.12) and (2.13) are equivalent to (2.16) and hence to

$$2\partial_{\dot{\mathbf{C}}_{\text{tr}}} \widehat{R}(\mathbf{C}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \ni \mathbf{T}.$$

The statement of the theorem will follow by proving directly that

$$-\frac{1}{2} \mathbf{T} \in \partial_{\dot{\mathbf{C}}_{\text{tr}}} \widehat{\psi}(\mathbf{C}, \mathbf{C}_{\text{tr}}, \theta) = \partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2}) + \partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta). \quad (3.4)$$

Let us work out the two terms in the above right-hand side separately. We shall preliminarily observe that, for all  $\mathbf{B} \in \mathbb{R}^{d \times d}$ , we have the following

$$\partial_{\mathbf{F}_{\text{tr}}} \mathbf{F}_{\text{tr}}^{-\top} : \mathbf{B} = -\mathbf{F}_{\text{tr}}^{-\top} \mathbf{B}^\top \mathbf{F}_{\text{tr}}^{-\top}, \quad \partial_{\mathbf{F}_{\text{tr}}} \mathbf{F}_{\text{tr}}^{-1} : \mathbf{B} = -\mathbf{F}_{\text{tr}}^{-1} \mathbf{B} \mathbf{F}_{\text{tr}}^{-1}, \quad (3.5)$$

$$(\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}}^\top : \mathbf{B})^\top = \partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B}, \quad (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B})^\top = \partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}}^\top : \mathbf{B}, \quad (3.6)$$

$$\begin{aligned} \partial_{\mathbf{F}_{\text{tr}}} (\mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1}) : \mathbf{B} &= -\mathbf{F}_{\text{tr}}^{-\top} \mathbf{B}^\top \mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1} - \mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1} \mathbf{B} \mathbf{F}_{\text{tr}}^{-1} \\ &= -\mathbf{F}_{\text{tr}}^{-\top} \mathbf{B}^\top \mathbf{C}_{\text{el}} - \mathbf{C}_{\text{el}} \mathbf{B} \mathbf{F}_{\text{tr}}^{-1} = \partial_{\mathbf{F}_{\text{tr}}^\top} (\mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1}) : \mathbf{B}^\top, \end{aligned} \quad (3.7)$$

$$\mathbf{B} = \partial_{\mathbf{C}_{\text{tr}}} \mathbf{C}_{\text{tr}} : \mathbf{B} = \partial_{\mathbf{C}_{\text{tr}}} (\mathbf{F}_{\text{tr}}^\top \mathbf{F}_{\text{tr}}) : \mathbf{B} = (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}}^\top : \mathbf{B}) \mathbf{F}_{\text{tr}} + \mathbf{F}_{\text{tr}}^\top (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B}). \quad (3.8)$$

In particular, relation (3.8) entails that, for all  $\mathbf{B} \in \mathbb{R}^{d \times d}$ ,

$$\mathbf{F}_{\text{tr}}^{-\top} \mathbf{B} \mathbf{F}_{\text{tr}}^{-1} = \mathbf{F}_{\text{tr}}^{-\top} (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}}^\top : \mathbf{B}) + (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B}) \mathbf{F}_{\text{tr}}^{-1}. \quad (3.9)$$

Hence, given  $\mathbf{B} \in \mathbb{R}^{d \times d}$  one has that

$$\begin{aligned}
\partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2}) : \mathbf{B} &= \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : \partial_{\mathbf{F}_{\text{tr}}} (\mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1}) : \partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B} \\
&= -\partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : \mathbf{F}_{\text{tr}}^{-\top} (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}}^{\top} : \mathbf{B}) \mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1} - \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : \mathbf{F}_{\text{tr}}^{-\top} \mathbf{C} \mathbf{F}_{\text{tr}}^{-1} (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B}) \mathbf{F}_{\text{tr}}^{-1} \\
&= -\partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} \mathbf{C}_{\text{el}} : \mathbf{F}_{\text{tr}}^{-\top} (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}}^{\top} : \mathbf{B}) - \mathbf{C}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B}) \mathbf{F}_{\text{tr}}^{-1} \\
&\stackrel{(3.9)}{=} -\mathbf{C}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : [\mathbf{F}_{\text{tr}}^{-\top} (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}}^{\top} : \mathbf{B}) + (\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B}) \mathbf{F}_{\text{tr}}^{-1}] \\
&= -\mathbf{C}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} : \mathbf{F}_{\text{tr}}^{-\top} \mathbf{B} \mathbf{F}_{\text{tr}}^{-1} = -\mathbf{F}_{\text{tr}}^{-1} \mathbf{C}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}} \mathbf{F}_{\text{tr}}^{-\top} : \mathbf{B} \\
&= -\frac{1}{2} \mathbf{F}_{\text{tr}}^{-1} \mathbf{M} \mathbf{F}_{\text{tr}}^{-\top} : \mathbf{B}. \tag{3.10}
\end{aligned}$$

In the second identity above we have used (3.7) by replacing  $\mathbf{B}$  by  $\partial_{\mathbf{C}_{\text{tr}}} \mathbf{F}_{\text{tr}} : \mathbf{B}$ .

Namely, we have finally checked that

$$\partial_{\mathbf{C}_{\text{tr}}} \hat{\psi} = \partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2}) + \partial_{\mathbf{C}_{\text{tr}}} \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta) = -\frac{1}{2}(\mathbf{M} - \mathbf{A}) \equiv -\frac{1}{2} \mathbf{T}$$

and (3.4) holds.  $\square$

**3.1. Dissipation distance.** Let us close this Section by observing that the dissipation functional  $\hat{R}$  defines a left-invariant Finsler metric. Hence, one can coordinate to  $\hat{R}$  a global metric by letting  $\hat{D} : \mathbb{R}^{d \times d} \times \mathbb{R}^{d \times d} \rightarrow [0, \infty]$  be defined by

$$\begin{aligned}
&\hat{D}(\mathbf{C}_{\text{tr},0}, \mathbf{C}_{\text{tr},1}) \\
&\doteq \inf \left\{ \int_0^1 \hat{R}(\mathbf{C}_{\text{tr}}, \dot{\mathbf{C}}_{\text{tr}}) \mid \mathbf{C}_{\text{tr}} \in C^1([0, 1]; \mathbb{R}^{d \times d}), \mathbf{C}_{\text{tr}}(0) = \mathbf{C}_{\text{tr},0}, \mathbf{C}_{\text{tr}}(1) = \mathbf{C}_{\text{tr},1} \right\}.
\end{aligned}$$

Note in particular that

$$\begin{aligned}
\hat{D}(\mathbf{C}_{\text{tr},0}, \mathbf{C}_{\text{tr},1}) &= \hat{D}(\mathbf{1}, \mathbf{C}_{\text{tr},1} \mathbf{C}_{\text{tr},0}^{-1}) \quad \forall \mathbf{C}_{\text{tr},0}, \mathbf{C}_{\text{tr},1} \in \mathbb{R}^{d \times d}, \\
\hat{D}(\mathbf{1}, \mathbf{C}_{\text{tr},1}) &< \infty \implies \mathbf{C}_{\text{tr},1} \in \text{SL}(d).
\end{aligned}$$

The interested reader is referred to [17, 36, 37] for additional details.

#### 4. EXISTENCE OF ENERGETIC SOLUTIONS

We shall now turn our attention to the existence of suitably weak solutions to the constitutive material relation (3.3). To this aim, assume to be given  $t \mapsto \theta(t) > 0$  and  $t \mapsto \mathbf{C}(t) \in \mathbb{R}_{\text{sym}}^{d \times d}$  and set for the sake of notational simplicity

$$e(t, \mathbf{C}_{\text{tr}}) \doteq \hat{\psi}(\mathbf{C}(t), \mathbf{C}_{\text{tr}}, \theta(t))$$

throughout. In order to make precise the solution notion we shall be dealing with we need to introduce the *stable states*  $\mathcal{S}(t)$  at time  $t \in [0, T]$  as

$$\mathcal{S}(t) \doteq \{ \mathbf{C}_{\text{tr}} \in \text{SL}_{\text{sym}}(d) \mid e(t, \mathbf{C}_{\text{tr}}) < \infty \text{ and } e(t, \mathbf{C}_{\text{tr}}) \leq e(t, \mathbf{B}) + \hat{D}(\mathbf{C}_{\text{tr}}, \mathbf{B}) \quad \forall \mathbf{B} \in \text{SL}_{\text{sym}}(d) \}. \tag{4.1}$$

An *energetic solution* [38, 49] corresponds to a trajectory  $\mathbf{C}_{\text{tr}} : [0, T] \rightarrow \mathbb{R}^{d \times d}$  such that  $\mathbf{C}_{\text{tr}}(0) = \mathbf{C}_{\text{tr},0}$ , where  $\mathbf{C}_{\text{tr},0}$  is some given initial datum, and

$$\mathbf{C}_{\text{tr}}(t) \in \mathcal{S}(t) \quad \forall t \in [0, T], \quad (4.2)$$

$$e(t, \mathbf{C}_{\text{tr}}(t)) + \text{Diss}_{[0,t]}(\mathbf{C}_{\text{tr}}) = e(0, \mathbf{C}_{\text{tr}}(0)) + \int_0^t \partial_t e(s, \mathbf{C}_{\text{tr}}(s)) ds \quad \forall t \in [0, T] \quad (4.3)$$

where the *total dissipation*  $\text{Diss}_{[0,t]}(\mathbf{C}_{\text{tr}})$  in the time interval  $[0, t]$  is given by

$$\text{Diss}_{[0,t]}(\mathbf{C}_{\text{tr}}) \doteq \sup \left\{ \sum_{i=1}^N \widehat{D}(\mathbf{C}_{\text{tr}}(t^{i-1}), \mathbf{C}_{\text{tr}}(t^i)) \mid 0 = t^0 < t^1 < \dots < t^N = t \right\}$$

the supremum being taken among all partitions of the interval  $[0, t]$ . Note that  $\text{Diss}_{[0,T]}(\mathbf{C}_{\text{tr}}) < \infty$  implies that  $\mathbf{C}_{\text{tr}}(t) \in \text{SL}(d)$  for all times. Moreover, from the finiteness of the energy for all times from (4.2), we deduce that all energetic solutions  $t \mapsto \mathbf{C}_{\text{tr}}(t)$  are such that

$$|\mathbf{E}_{\text{tr}}(t)| = \frac{1}{2} |\mathbf{C}_{\text{tr}}(t) - \mathbf{1}| \leq \epsilon_L \quad \forall t \in [0, T].$$

In particular, the maximal-inelastic-strain constraint is fulfilled at all times. Let us now formulate the assumptions on  $\mathbf{C}$  and  $\theta$  as

$$\mathbf{C} \in W^{1,1}(0, T; \mathbb{R}_{\text{sym}}^{d \times d}), \quad \det \mathbf{C}(t) \geq \alpha_0 > 0 \quad \forall t \in [0, T], \quad (4.4)$$

$$\theta \in W^{1,1}(0, T). \quad (4.5)$$

**Theorem 4.1** (Existence of energetic solutions). *Let (4.4)-(4.5) hold and  $\mathbf{C}_{\text{tr},0} \in \mathcal{S}(0)$ . Then, there exist an energetic solution of (3.3).*

The proof of this theorem is developed in the remainder of this section and follows by adapting the by-now classical argument of [49]. In particular, we shall proceed by time-discretization. An interesting by-product of this procedure relies in the possibility of approximating the limit problem constructively. Note that some numerical computation for this model has been provided in [24]. Here, we complement the discussion from [24] by rigorously proving convergence of the numerical scheme.

**4.1. Incremental minimization.** Assume to be given a partition of  $[0, T]$  which we identify with the corresponding vector  $\boldsymbol{\tau} = (\tau^1, \dots, \tau^{N_\tau})$  of strictly positive time-steps. Note that we indicate with superscripts the elements of a generic vector. In particular  $\tau^j$  represents the  $j$ -th component of the vector  $\boldsymbol{\tau}$  (and not the  $j$ -th power of the scalar  $\tau$ ).

We let  $t_\tau^0 \doteq 0$  and define recursively

$$t_\tau^i \doteq t_\tau^{i-1} + \tau^i, \quad I_\tau^i \doteq [t_\tau^{i-1}, t_\tau^i) \quad \text{for } i = 1, \dots, N_\tau.$$

Let the symbol  $\bar{\tau} \doteq \max_{i=1, \dots, N_\tau} \tau^i$  denote the maximum time-step (fineness of the partition). We will make use of the notation  $(\mathbf{B}_\tau^0, \dots, \mathbf{B}_\tau^{N_\tau})$  for elements in  $(\mathbb{R}^{d \times d})^{N_\tau+1}$  and let  $\mathbf{B}_\tau : [0, T] \rightarrow \mathbb{R}^{d \times d}$  be the corresponding piecewise constant interpolant on the intervals  $I_\tau^i$ , namely  $\mathbf{B}_\tau(t) \doteq \mathbf{B}_\tau^{i-1}$  for all  $t \in I_\tau^i$ ,  $i = 1, \dots, N_\tau$  and  $\mathbf{B}_\tau(T) \doteq \mathbf{B}_\tau^{N_\tau}$ .

As we are given  $(\mathbf{C}, \theta) : [0, T] \rightarrow \mathbb{R}_{\text{sym}}^{d \times d} \times (0, \infty)$ , we define  $(\mathbf{C}_\tau^i, \theta_\tau^i) \doteq (\mathbf{C}(t_\tau^i), \theta(t_\tau^i))$ . Then, we look for a vector  $(\mathbf{C}_{\text{tr},\tau}^0, \dots, \mathbf{C}_{\text{tr},\tau}^{N_\tau}) \in (\text{SL}_{\text{sym}}(d))^{N_\tau+1}$  such that

$$\mathbf{C}_{\text{tr},\tau}^0 = \mathbf{C}_{\text{tr},0}, \quad (4.6)$$

$$\mathbf{C}_{\text{tr},\tau}^i \in \text{Arg min} \left\{ e(t_\tau^i, \mathbf{C}_{\text{tr}}) + \widehat{D}(\mathbf{C}_{\text{tr},\tau}^{i-1}, \mathbf{C}_{\text{tr}}) \mid \mathbf{C}_{\text{tr}} \in \text{SL}_{\text{sym}}(d) \right\} \quad \text{for } i = 1, \dots, N_\tau. \quad (4.7)$$

Hence, the solution  $\mathbf{C}_{\text{tr},\tau}$  is obtained by *sequentially* minimizing on  $\text{SL}_{\text{sym}}(d)$

$$\mathbf{C}_{\text{tr}} \mapsto \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}_{\tau}^i \mathbf{C}_{\text{tr}}^{-1/2}) + \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta_{\tau}^i) + \widehat{D}(\mathbf{C}_{\text{tr},\tau}^{i-1}, \mathbf{C}_{\text{tr}}).$$

Such incremental solution clearly exists as the above functional turns out to be coercive and lower semicontinuous and  $\text{SL}_{\text{sym}}(d)$  is closed. In particular,  $\mathbf{E}_{\text{tr},\tau}^i \doteq (\mathbf{C}_{\text{tr},\tau}^i - \mathbf{1})/2$  is such that  $|\mathbf{E}_{\text{tr},\tau}^i| \leq \epsilon_L$  for all  $i = 1, \dots, N_{\tau}$ .

**4.2. Discrete stability and estimates.** Let us show that  $\mathbf{C}_{\text{tr},\tau}^i \in \mathcal{S}(t_{\tau}^i)$  for  $i = 1, \dots, N_{\tau}$ . By using the minimality (4.7) and the triangle inequality for  $\widehat{D}$ , we have that, for all  $\mathbf{B} \in \text{SL}_{\text{sym}}(d)$ ,

$$\begin{aligned} e(t_{\tau}^i, \mathbf{C}_{\text{tr},\tau}^i) + \widehat{D}(\mathbf{C}_{\text{tr},\tau}^{i-1}, \mathbf{C}_{\text{tr},\tau}^i) &\leq e(t_{\tau}^i, \mathbf{B}) + \widehat{D}(\mathbf{C}_{\text{tr},\tau}^{i-1}, \mathbf{B}) \\ &\leq e(t_{\tau}^i, \mathbf{B}) + \widehat{D}(\mathbf{C}_{\text{tr},\tau}^{i-1}, \mathbf{C}_{\text{tr},\tau}^i) + \widehat{D}(\mathbf{C}_{\text{tr},\tau}^i, \mathbf{B}) \end{aligned}$$

whence stability follows. Furthermore, again by minimality (4.7) the following inequality holds

$$e(t_{\tau}^i, \mathbf{C}_{\text{tr},\tau}^i) + \widehat{D}(\mathbf{C}_{\text{tr},\tau}^{i-1}, \mathbf{C}_{\text{tr},\tau}^i) \leq e(t_{\tau}^{i-1}, \mathbf{C}_{\text{tr},\tau}^{i-1}) + \int_{t_{\tau}^{i-1}}^{t_{\tau}^i} \partial_s e(s, \mathbf{C}_{\text{tr},\tau}^{i-1}) ds.$$

By summing up we get the *discrete upper energy estimate* for the piecewise constant  $\mathbf{C}_{\text{tr},\tau}$

$$\begin{aligned} e(t_{\tau}^m, \mathbf{C}_{\text{tr},\tau}(t_{\tau}^m)) + \text{Diss}_{[t_{\tau}^i, t_{\tau}^m]}(\mathbf{C}_{\text{tr},\tau}) \\ \leq e(t_{\tau}^i, \mathbf{C}_{\text{tr},\tau}(t_{\tau}^i)) + \int_{t_{\tau}^i}^{t_{\tau}^m} \partial_s e(s, \mathbf{C}_{\text{tr},\tau}(s)) ds \quad \text{for } i \leq m. \end{aligned} \quad (4.8)$$

Our next aim is that of controlling the *power* of external actions. In particular, for all given  $\mathbf{C}_{\text{tr}} \in K \doteq \{\mathbf{C}_{\text{tr}} \in \text{SL}_{\text{sym}}(d) \mid |\mathbf{C}_{\text{tr}} - \mathbf{1}_2| \leq 2\epsilon_L\}$  (recall (2.7)), we have

$$\partial_t e(t, \mathbf{C}_{\text{tr}}) = \partial_{\mathbf{C}} \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2}) : \dot{\mathbf{C}}(t) + \partial_t \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta(t)). \quad (4.9)$$

Due to assumption (4.5) and to the explicit form (2.7) of the inelastic energy  $\psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta)$ , we have that  $t \mapsto \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta(t)) \in W^{1,1}(0, T)$  and

$$\partial_t \psi_{\text{tr}}(\mathbf{C}_{\text{tr}}, \theta(t)) = bH(\theta(t) - \theta_M) |\mathbf{E}_{\text{tr}}| \dot{\theta}(t) \quad \text{for a.e. } t \in (0, T) \quad (4.10)$$

where  $H$  is the Heaviside function. As for the first term in the right-hand side of (4.9) we compute by (2.2)

$$\begin{aligned} \partial_{\mathbf{C}} \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2}) &= \partial_{\mathbf{A}} \psi_{\text{el}}(\mathbf{A})|_{\mathbf{A}=\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2}} : \partial_{\mathbf{C}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2}) \\ &= \mathbf{C}_{\text{tr}}^{-1/2} \partial_{\mathbf{A}} \psi_{\text{el}}(\mathbf{A})|_{\mathbf{A}=\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2}}. \end{aligned} \quad (4.11)$$

Let us observe that assumption (4.4) entails in particular that  $\mathbf{C} \in L^{\infty}(0, T; \mathbb{R}_{\text{sym}}^{d \times d})$ . Moreover, we have that

$$\mathbf{C}_{\text{tr}} \in K \Rightarrow |\mathbf{C}_{\text{tr}}| + |\mathbf{C}_{\text{tr}}^{-1}| \leq c_K$$

where  $c_K > 0$  depends on data only. From the smoothness of the square root [27, pag. 23] an analogous bound holds true for  $|\mathbf{C}_{\text{tr}}^{1/2}| + |\mathbf{C}_{\text{tr}}^{-1/2}|$ . In particular, given the above bounds, one can check that  $|\mathbf{F}_{\text{el}}| + |\mathbf{F}_{\text{el}}^{-1}|$  is also a priori bounded in terms of data and  $|\mathbf{C}(t)|$ . Now, we remark that, for all  $\mathbf{B} \in \mathbb{R}^{d \times d}$ , one has

$$\partial_{\mathbf{F}_{\text{el}}} W(\mathbf{F}_{\text{el}}) \mathbf{F}_{\text{el}}^{\top} : \mathbf{B} = \mathbf{F}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}}(\mathbf{C}_{\text{el}}) \mathbf{F}_{\text{el}}^{\top} : (\mathbf{B} + \mathbf{B}^{\top}).$$

Hence, we can control the first term in the right-hand side of (4.9) as follows (recall (3.1), which implies  $\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C} \mathbf{C}_{\text{tr}}^{-1/2} = \mathbf{R}^\top \mathbf{C}_{\text{el}} \mathbf{R}$ )

$$\begin{aligned}
& |\partial_{\mathbf{C}} \psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2}) : \dot{\mathbf{C}}(t)| \\
&= |\mathbf{F}_{\text{el}} \partial_{\mathbf{A}} \psi_{\text{el}}(\mathbf{A})|_{\mathbf{A}=\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{F}_{\text{el}}^\top : \mathbf{F}_{\text{el}}^{-\top} \mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}(t) \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{F}_{\text{el}}^{-1}}| \\
&= |\mathbf{F}_{\text{el}} \mathbf{R}^\top \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}}(\mathbf{C}_{\text{el}}) \mathbf{R} \mathbf{F}_{\text{el}}^\top : \mathbf{F}_{\text{el}}^{-\top} \mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}(t) \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{F}_{\text{el}}^{-1}}| \\
&= |\mathbf{F}_{\text{el}} \partial_{\mathbf{C}_{\text{el}}} \psi_{\text{el}}(\mathbf{C}_{\text{el}}) \mathbf{F}_{\text{el}}^\top : \mathbf{F}_{\text{el}}^{-\top} \mathbf{R} \mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}(t) \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{R}^\top \mathbf{F}_{\text{el}}^{-1}}| \\
&= \frac{1}{2} |\partial_{\mathbf{F}_{\text{el}}} W(\mathbf{F}_{\text{el}}) \mathbf{F}_{\text{el}}^\top : \mathbf{F}_{\text{el}}^{-\top} \mathbf{R} \mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}(t) \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{R}^\top \mathbf{F}_{\text{el}}^{-1}}| \\
&\leq \frac{1}{2} c_0 (W(\mathbf{F}_{\text{el}}) + 1) |\mathbf{F}_{\text{el}}^{-\top} \mathbf{R} \mathbf{C}_{\text{tr}}^{-1/2} \dot{\mathbf{C}}(t) \mathbf{C}_{\text{tr}}^{-1/2} \mathbf{R}^\top \mathbf{F}_{\text{el}}^{-1}}| \\
&\leq c(\psi_{\text{el}}(\mathbf{C}_{\text{tr}}^{-1/2} \mathbf{C}(t) \mathbf{C}_{\text{tr}}^{-1/2}) + 1) |\dot{\mathbf{C}}(t)|.
\end{aligned}$$

where  $c$  depends on data only. Hence, we can conclude that

$$|e(t, \mathbf{C}_{\text{tr}})| \leq \gamma(t)(1 + e(t, \mathbf{C}_{\text{tr}})) \quad (4.12)$$

where  $t \mapsto \gamma(t) \doteq c_e(|\dot{\mathbf{C}}(t)| + |\dot{\theta}(t)|) \in L^1(0, T)$  and  $c_e > 0$  depends on data only. Moreover, note that for almost all times  $t \in [0, T]$  the power  $\mathbf{C}_{\text{tr}} \mapsto \partial_t e(t, \mathbf{C}_{\text{tr}})$  turns out to be continuous on  $K$  as a consequence of the smoothness of  $\psi_{\text{el}}$  and the continuity of the inverse on  $\text{SL}(d)$  and of the square root in  $\mathbb{R}_{\text{sym}}^{d \times d}$ .

Now, from the minimality (4.7) we deduce that the piecewise constant  $\mathbf{C}_{\text{tr}, \tau}$  satisfies  $\mathbf{C}_{\text{tr}, \tau}(t) \in K$  for every  $t \in [0, T]$ . Moreover, owing to the bound (4.12), the discrete upper energy estimate (4.8) entails via Gronwall (see [38]) that

$$\sup_{\tau} \left( \sup_{t \in [0, T]} e(t, \mathbf{C}_{\text{tr}, \tau}(t)) + \text{Diss}_{[0, T]}(\mathbf{C}_{\text{tr}, \tau}) \right) < \infty \quad (4.13)$$

Let us now take a sequence of partitions  $\tau_k$  such that  $\bar{\tau}_k \rightarrow 0$  as  $k \rightarrow \infty$ . Let  $\mathbf{C}_{\text{tr}}^k \doteq \mathbf{C}_{\text{tr}, \tau_k}$  be the corresponding discrete solutions. From the bound (4.13) and Helly's selection principle (see, e.g., [39]) we can deduce the existence of a (not relabeled) subsequence  $\mathbf{C}_{\text{tr}}^k$  and of a function  $\mathbf{C}_{\text{tr}} \in BV_{\widehat{D}}([0, T]; \text{SL}_{\text{sym}}(d)) \doteq \{t \in [0, T] \mapsto \mathbf{C}_{\text{tr}}(t) \in \text{SL}_{\text{sym}}(d) \mid \text{Diss}_{[0, T]}(\mathbf{C}_{\text{tr}}) < \infty\}$  such that

$$\mathbf{C}_{\text{tr}}^k(t) \rightarrow \mathbf{C}_{\text{tr}}(t) \quad \text{as } k \rightarrow \infty \quad \forall t \in [0, T].$$

In particular, as  $|\mathbf{C}_{\text{tr}}^k(t) - \mathbf{1}| \leq 2\epsilon_L$  for all times  $t \in [0, T]$ , the latter convergence entails that  $|\mathbf{C}_{\text{tr}}(t) - \mathbf{1}| \leq 2\epsilon_L$  for all  $t \in [0, T]$  as well. Hence, the limit function  $\mathbf{C}_{\text{tr}}$  fulfills the constraint  $|\mathbf{E}_{\text{tr}}| = |\mathbf{C}_{\text{tr}} - \mathbf{1}|/2 \leq \epsilon_L$  for all times. We now aim at showing that  $\mathbf{C}_{\text{tr}}$  is an energetic solution of (3.3), namely that it satisfies the stability condition (4.2) and the energy balance (4.3).

**Stability of the limit function.** We first show that the set  $\mathcal{S}_{[0, T]} \doteq \{(t, \mathbf{C}_{\text{tr}}) \in [0, T] \times \text{SL}_{\text{sym}}(d) : \mathbf{C}_{\text{tr}} \in \mathcal{S}(t)\}$  is closed in  $[0, T] \times \text{SL}_{\text{sym}}(d)$ . Let us take  $(t_n, \mathbf{C}_{\text{tr}}^{(n)}) \in \mathcal{S}_{[0, T]}$  such that  $t_n \rightarrow t^*$  in  $[0, T]$  and  $\mathbf{C}_{\text{tr}}^{(n)} \rightarrow \mathbf{C}_{\text{tr}}^*$  in  $\text{SL}_{\text{sym}}(d)$ . Since  $\mathbf{C}_{\text{tr}}^{(n)} \in \mathcal{S}(t_n)$ , we have  $e(t_n, \mathbf{C}_{\text{tr}}^{(n)}) < \infty$  and

$$e(t_n, \mathbf{C}_{\text{tr}}^{(n)}) \leq e(t_n, \widehat{\mathbf{C}}_{\text{tr}}) + \widehat{D}(\mathbf{C}_{\text{tr}}^{(n)}, \widehat{\mathbf{C}}_{\text{tr}}) \quad \forall \widehat{\mathbf{C}}_{\text{tr}} \in \text{SL}_{\text{sym}}(d).$$

By passing to the limit for  $n \rightarrow \infty$  and using the continuity of  $\widehat{\psi}$  (restricted to  $\mathbb{R}_{\text{sym}}^{d \times d} \times K \times \mathbb{R}$ ), we immediately get that  $(t^*, \mathbf{C}_{\text{tr}}^*) \in \mathcal{S}_{[0, T]}$ . Let us now fix  $t \in [0, T]$  and define  $s_k^t \doteq \max\{t_{\tau_k}^i \mid t_{\tau_k}^i \leq t\}$ . We have that  $s_k^t \rightarrow t$  and  $\mathbf{C}_{\text{tr}}^k(s_k^t) = \mathbf{C}_{\text{tr}}^k(t) \rightarrow \mathbf{C}_{\text{tr}}(t)$  as  $k \rightarrow \infty$ . Since  $\mathbf{C}_{\text{tr}}^k(s_k^t) \in \mathcal{S}(s_k^t)$ , by the closedness of  $\mathcal{S}_{[0, T]}$  we have that  $\mathbf{C}_{\text{tr}}(t) \in \mathcal{S}(t)$ .

**Upper energy estimate.** Along with the above notation, the discrete upper energy estimate (4.8) can be rewritten as

$$e(s_k^t, \mathbf{C}_{\text{tr}}^k(s_k^t)) + \text{Diss}_{[0, s_k^t]}(\mathbf{C}_{\text{tr}}^k) \leq e(0, \mathbf{C}_{\text{tr},0}) + \int_0^{s_k^t} \partial_s e(s, \mathbf{C}_{\text{tr}}^k(s)) ds.$$

By observing that  $\text{Diss}_{[0, s_k^t]}(\mathbf{C}_{\text{tr}}^k) = \text{Diss}_{[0, t]}(\mathbf{C}_{\text{tr}}^k)$ , passing to the limit as  $k \rightarrow \infty$ , and exploiting the bound (4.12), relation (4.13), the lower semicontinuity of the functional  $\text{Diss}_{[0, t]}$ , and the Lebesgue's Dominated Convergence Theorem, we deduce the *upper energy estimate*

$$e(t, \mathbf{C}_{\text{tr}}(t)) + \text{Diss}_{[0, t]}(\mathbf{C}_{\text{tr}}) \leq e(0, \mathbf{C}_{\text{tr},0}) + \int_0^t \partial_s e(s, \mathbf{C}_{\text{tr}}(s)) ds \quad \forall t \in [0, T].$$

**Lower energy estimate.** Let us take a sequence of partitions  $\tau_m$  of the interval  $[0, t]$ , with  $\bar{\tau}_m \rightarrow 0$  as  $m \rightarrow \infty$ . Since  $\mathbf{C}_{\text{tr}}(t) \in \mathcal{S}(t)$ , for every  $t \in [0, T]$ , we have (setting for brevity  $N_m \doteq N_{\tau_m}$  and  $t_m^j \doteq t_{\tau_m}^j$ )

$$\begin{aligned} & e(t_m^j, \mathbf{C}_{\text{tr}}(t_m^j)) + \widehat{D}(\mathbf{C}_{\text{tr}}(t_m^{j-1}), \mathbf{C}_{\text{tr}}(t_m^j)) \\ &= e(t_m^{j-1}, \mathbf{C}_{\text{tr}}(t_m^j)) + \int_{t_m^{j-1}}^{t_m^j} \partial_s e(s, \mathbf{C}_{\text{tr}}(t_m^j)) ds + \widehat{D}(\mathbf{C}_{\text{tr}}(t_m^{j-1}), \mathbf{C}_{\text{tr}}(t_m^j)) \\ &\geq e(t_m^{j-1}, \mathbf{C}_{\text{tr}}(t_m^{j-1})) + \int_{t_m^{j-1}}^{t_m^j} \partial_s e(s, \mathbf{C}_{\text{tr}}(t_m^j)) ds. \end{aligned}$$

Summing up for  $j = 1, \dots, N_m$  we deduce that

$$\begin{aligned} & e(t, \mathbf{C}_{\text{tr}}(t)) - e(0, \mathbf{C}_{\text{tr},0}) + \text{Diss}_{[0, t]}(\mathbf{C}_{\text{tr}}) \\ &\geq \sum_{j=1}^{N_m} \left[ e(t_m^j, \mathbf{C}_{\text{tr}}(t_m^j)) - e(t_m^{j-1}, \mathbf{C}_{\text{tr}}(t_m^{j-1})) \right] + \sum_{j=1}^{N_m} \widehat{D}(\mathbf{C}_{\text{tr}}(t_m^{j-1}), \mathbf{C}_{\text{tr}}(t_m^j)) \\ &\geq \int_0^t \partial_s e(s, \bar{\mathbf{C}}_{\text{tr}}^{(m)}(s)) ds, \end{aligned} \tag{4.14}$$

where  $\bar{\mathbf{C}}_{\text{tr}}^{(m)}$  is defined as  $\bar{\mathbf{C}}_{\text{tr}}^{(m)}(t) = \mathbf{C}_{\text{tr}}(t_m^j)$  for every  $t \in (t_m^{j-1}, t_m^j]$ . By recalling (4.9)-(4.10), the integral on the right-hand side is given by the sum of two contributions, namely

$$\begin{aligned} \int_0^t \partial_s e(s, \bar{\mathbf{C}}_{\text{tr}}^{(m)}(s)) ds &= \int_0^t bH(\theta(s) - \theta_M) |\bar{\mathbf{E}}_{\text{tr}}^{(m)}(s)| \dot{\theta}(s) ds \\ &\quad + \int_0^t \partial_{\mathbf{C}} \psi_{\text{el}}((\bar{\mathbf{C}}_{\text{tr}}^{(m)}(s))^{-1/2} \mathbf{C}(\bar{\mathbf{C}}_{\text{tr}}^{(m)}(s))^{-1/2}) \Big|_{\mathbf{C}=\mathbf{C}(s)} : \dot{\mathbf{C}}(s) ds \end{aligned}$$

where  $\bar{\mathbf{E}}_{\text{tr}}^{(m)} = (\bar{\mathbf{C}}_{\text{tr}}^{(m)} - \mathbf{1}_2)/2$ . As  $\mathbf{C}_{\text{tr}} \in BV_{\widehat{D}}([0, T]; \text{SL}_{\text{sym}}(d))$ , we have that  $\mathbf{C}_{\text{tr}}$  is continuous on  $[0, T]$  with the exception of at most a countable set of points [39, Thm. 3.3]. Hence, we have  $\bar{\mathbf{C}}_{\text{tr}}^{(m)}(t) \rightarrow \mathbf{C}_{\text{tr}}(t)$  for a.e.  $t \in (0, T)$ . We can then apply Lebesgue's Dominated Convergence Theorem to conclude that

$$\int_0^t bH(\theta(s) - \theta_M) |\bar{\mathbf{E}}_{\text{tr}}^{(m)}(s)| \dot{\theta}(s) ds \rightarrow \int_0^t bH(\theta(s) - \theta_M) |\mathbf{E}_{\text{tr}}(s)| \dot{\theta}(s) ds$$

Next, by recalling the continuity of the power term and assumption (4.4), we may use again Lebesgue's theorem and show that

$$\begin{aligned} & \int_0^t \partial_{\mathbf{C}} \psi_{\text{el}}((\overline{\mathbf{C}}_{\text{tr}}^{(m)}(s))^{-1/2} \mathbf{C}(s) (\overline{\mathbf{C}}_{\text{tr}}^{(m)}(s))^{-1/2}) : \dot{\mathbf{C}}(s) \, ds \\ & \rightarrow \int_0^t \partial_{\mathbf{C}} \psi_{\text{el}}((\mathbf{C}_{\text{tr}}(s))^{-1/2} \mathbf{C}(s) (\mathbf{C}_{\text{tr}}(s))^{-1/2}) : \dot{\mathbf{C}}(s) \, ds. \end{aligned}$$

Hence, the integral on the right-hand side of (4.14) converges to

$$\int_0^t bH(\theta(s) - \theta_M) |\mathbf{E}_{\text{tr}}(s)| \dot{\theta}(s) \, ds + \int_0^t \partial_{\mathbf{C}} \psi_{\text{el}}((\mathbf{C}_{\text{tr}}(s))^{-1/2} \mathbf{C}(s) (\mathbf{C}_{\text{tr}}(s))^{-1/2}) : \dot{\mathbf{C}}(s) \, ds$$

and, by taking the limit  $m \rightarrow \infty$ , we get the desired lower energy estimate

$$e(t, \mathbf{C}_{\text{tr}}(t)) + \text{Diss}_{[0,t]}(\mathbf{C}_{\text{tr}}) \geq e(0, \mathbf{C}_{\text{tr},0}) + \int_0^t \partial_s e(s, \mathbf{C}_{\text{tr}}(s)) \, ds \quad \forall t \in [0, T].$$

In particular, we have proved that  $\mathbf{C}_{\text{tr}}$  fulfills both the stability (4.2) and the energy equality (4.3). Namely,  $\mathbf{C}_{\text{tr}}$  is an energetic solution.

#### ACKNOWLEDGMENTS

The Authors are indebted to Alexander Mielke for some interesting discussion on this model. U.S. acknowledges the partial support of FP7-IDEAS-ERC-StG Grant #200497 (*BioSMA*), the CNR-AVČR joint project *SmartMath*, and the Alexander von Humboldt Foundation.

#### REFERENCES

- [1] J. Arghavani, F. Auricchio, R. Naghdabadi, and A. Reali. On the robustness and efficiency of integration algorithms for a 3D finite strain phenomenological SMA constitutive model. *Internat. J. Numer. Meth. Engrg.*, 85 (2011) 107-134.
- [2] J. Arghavani, F. Auricchio, R. Naghdabadi, A. Reali, and S. Sohrabpour. A 3D finite strain phenomenological constitutive model for shape memory alloys considering martensite reorientation. *Contin. Mech. Thermodyn.*, 22 (2010) 345-362.
- [3] F. Auricchio, A.-L. Bessoud, A. Reali, and U. Stefanelli, A phenomenological model for the magnetomechanical response of magnetic shape memory alloys single crystals, (2011), in preparation.
- [4] F. Auricchio, A.-L. Bessoud, A. Reali, and U. Stefanelli, A three-dimensional phenomenological models for magnetic shape memory alloys, *GAMM-Mitt.*, 34 (2011) 1:90-96.
- [5] F. Auricchio, A. Mielke, and U. Stefanelli, A rate-independent model for the isothermal quasi-static evolution of shape-memory materials, *Math. Models Meth. Appl. Sci.*, 18 (2008) 1:125-164.
- [6] F. Auricchio and L. Petrini, Improvements and algorithmical considerations on a recent three-dimensional model describing stress-induced solid phase transformations, *Internat. J. Numer. Methods Engrg.*, 55 (2002) 1255-1284.
- [7] F. Auricchio and L. Petrini, A three-dimensional model describing stress-temperature induced solid phase transformations. Part I: solution algorithm and boundary value problems, *Internat. J. Numer. Methods Engrg.*, 61 (2004) 807-836.
- [8] F. Auricchio and L. Petrini, A three-dimensional model describing stress-temperature induced solid phase transformations. Part II: thermomechanical coupling and hybrid composite applications, *Internat. J. Numer. Methods Engrg.*, 61 (2004) 716-737.
- [9] F. Auricchio, A. Reali, and U. Stefanelli, A phenomenological 3D model describing stress-induced solid phase transformations with permanent inelasticity, in *Topics on Mathematics for Smart Systems (Rome, 2006)*, 1-14, World Sci. Publishing, 2007.
- [10] F. Auricchio, A. Reali, and U. Stefanelli, A three-dimensional model describing stress-induced solid phase transformation with permanent inelasticity, *Internat. J. Plast.*, 23 (2007) 207-226.
- [11] F. Auricchio, A. Reali, and U. Stefanelli, A macroscopic 1D model for shape memory alloys including asymmetric behaviors and transformation-dependent elastic properties, *Comput. Methods Appl. Mech. Engrg.*, 198 (2009) 1631-1637.

- [12] F. Auricchio and E. Sacco, A one-dimensional model for superelastic shape-memory alloys with different elastic properties between austenite and martensite, *Int. J. Non-Linear Mech.*, 32 (1997) 1101-1114.
- [13] F. Auricchio and R. L. Taylor. Shape-memory alloys: modelling and numerical simulations of the finite-strain superelastic behavior. *Comput. Methods Appl. Mech. Engrg.*, 143 (1997) 1-2:175194.
- [14] A.-L. Bessoud and U. Stefanelli, Magnetic shape memory alloys: three-dimensional modeling and analysis, *Math. Models Meth. Appl. Sci.*, 21 (2011) 5: 1043–1069.
- [15] A.-L. Bessoud, M. Kružík, and U. Stefanelli, A macroscopic model for magnetic shape memory alloys, Preprint IMATI-CNR, 23PV10/21/0 (2010).
- [16] H. Brezis. *Opérateurs maximaux monotones et semi-groupes de contractions dans les espaces de Hilbert*, no. 5 in North Holland Math. Studies, North-Holland, Amsterdam, 1973.
- [17] C. Carstensen, K. Hackl, and A. Mielke, Non-convex potentials and microstructures in finite-strain plasticity. *R. Soc. Lond. Proc. Ser. A Math. Phys. Eng. Sci.*, 458 (2002) 2018:299–317.
- [18] D. Christ and S. Reese. A finite element model for shape memory alloys considering thermomechanical couplings at large strains. *Int. J. Solids Struct.*, 46 (2009) 20:3694–3709.
- [19] T. W. Duerig, K. N. Melton, D. Stökel, C. M. Wayman editors, *Engineering aspects of shape memory alloys*, Butterworth-Heinemann, 1990.
- [20] T. W. Duerig, A. R. Pelton editors, *SMST-2003 Proceedings of the International Conference on Shape Memory and Superelastic Technology Conference*, ASM International, 2003.
- [21] M. Eleuteri, L. Lussardi, and U. Stefanelli, A rate-independent model for permanent inelastic effects in shape memory materials, *Netw. Heterog. Media*, 6 (2011) 1:145–165.
- [22] M. Eleuteri, L. Lussardi, and U. Stefanelli, Thermal control of the Souza-Auricchio model for shape memory alloys, Preprint IMATI-CNR 6PV11/4/0, 2011
- [23] V. Evangelista, S. Marfia, and E. Sacco, Phenomenological 3D and 1D consistent models for shape-memory alloy materials. *Comput. Mech.*, 44 (2009) 3:405–421.
- [24] V. Evangelista, S. Marfia, and E. Sacco, A 3D SMA constitutive model in the framework of finite strain, *Internat. J. Numer. Methods Engrg.*, 81 (2010) 6:761–785.
- [25] M. Frémond, Matériaux à mémoire de forme, *C. R. Acad. Sci. Paris Sér. II Méc. Phys. Chim. Sci. Univers Sci. Terre*, 304 (1987) 239–244.
- [26] M. Frémond, *Non-smooth Thermomechanics*, Springer-Verlag, Berlin, 2002.
- [27] M. E. Gurtin, *An introduction to continuum mechanics*. Mathematics in Science and Engineering, 158. Academic Press, Inc., New York-London, 1981.
- [28] D. Helm and P. Haupt, Shape memory behaviour: modelling within continuum thermomechanics, *Internat. J. Solids Structures*, 40 (2003) 827–849.
- [29] P. Krejčí and U. Stefanelli, Existence and nonexistence for the full thermomechanical Souza-Auricchio model of shape memory wires. *Math. Mech. Solids*, (2011), to appear.
- [30] P. Krejčí and U. Stefanelli, Well-posedness of a thermo-mechanical model for shape memory alloys under tension. *M2AN Math. Model. Numer. Anal.*, (2011), to appear.
- [31] D. C. Lagoudas, P. B. Entchev, P. Popov, E. Patoor, L. C. Brinson, X. Gao, Shape memory alloys, Part II: Modeling of polycrystals, *Mech. Materials*, 38 (2006) 391–429.
- [32] M. Panico and L. Brinson. A three-dimensional phenomenological model for martensite reorientation in shape memory alloys. *J. Mech. Phys. Solids*, 55 (2007) 11:2491–2511.
- [33] P. Popov and D. C. Lagoudas, A 3-D constitutive model for shape memory alloys incorporating pseudoelasticity and detwinning of self-accommodated martensite, *Internat. J. Plast.*, 23 (2007) 1679–1720.
- [34] E. Lee, Elastic-plastic deformation at finite strains, *J. Applied Mechanics*, 36 (1969) 1–6.
- [35] V. I. Levitas, Thermomechanical theory of martensitic phase transformations in inelastic materials, *Internat. J. Solids Structures*, 35 (1998) 889–940.
- [36] A. Mielke, Finite elastoplasticity Lie groups and geodesics on  $SL(d)$ , in *Geometry, mechanics, and dynamics*, 61–90, Springer, New York, 2002.
- [37] A. Mielke, Energetic formulation of multiplicative elasto-plasticity using dissipation distances, *Contin. Mech. Thermodyn.*, 15 (2003) 4:351–382.
- [38] A. Mielke, Evolution in rate-independent systems (Ch. 6), nn C. Dafermos and E. Feireisl, editors, *Handbook of Differential Equations, Evolutionary Equations, vol. 2*, 461–559. Elsevier B.V., Amsterdam, 2005.
- [39] A. Mainik and A. Mielke. Existence results for energetic models for rate-independent systems. *Calc. Var. Partial Differential Equations*, 22 (2005) 1:73–99.
- [40] A. Mainik and A. Mielke. Global existence for rate-independent gradient plasticity at finite strain. *J. Nonlinear Sci.*, 19 (2009) 221–248.
- [41] A. Mielke. A new approach to elasto-plasticity using energy and dissipation functionals. In *Applied Mathematics entering the 21st century*, 315–335, SIAM, Philadelphia, PA, 2004.

- [42] A. Mielke. Existence of minimizers in incremental elasto-plasticity with finite strains. *SIAM J. Math. Anal.*, 36 (2004) 2:384–404.
- [43] A. Mielke. Energetic formulation of multiplicative elasto-plasticity using dissipation distances. *Contin. Mech. Thermodyn.*, 15 (2003) 4:351–382.
- [44] A. Mielke and S. Müller. Lower semicontinuity and existence of minimizers in incremental finite-strain elastoplasticity. *ZAMM Z. Angew. Math. Mech.*, 86 (2006) 3:233–250.
- [45] A. Mielke, L. Paoli, and A. Petrov, On existence and approximation for a 3D model of thermally-induced phase transformations in shape-memory alloys, *SIAM J. Math. Anal.*, 41 (2009) 4:1388–1414.
- [46] A. Mielke, L. Paoli, A. Petrov, and U. Stefanelli, Error estimates for discretizations of a rate-independent variational inequality, *SIAM J. Numer. Anal.*, 48 (2010) 5: 1625–1646.
- [47] A. Mielke, L. Paoli, A. Petrov, and U. Stefanelli, Error bounds for space-time discretizations of a 3D model for shape-memory materials, Proceedings of the IUTAM Symposium on *Variational Concepts with Applications to the Mechanics of Materials* (Bochum 2008), IUTAM Bookseries, Springer, 2009.
- [48] A. Mielke and A. Petrov, Thermally driven phase transformation in shape-memory alloys, *Adv. Math. Sci. Appl.*, 17 (2007) 160–182.
- [49] A. Mielke and F. Theil, On rate-independent hysteresis models. *NoDEA Nonlinear Differential Equations Appl.*, 11 (2004) 151–189.
- [50] C. Müller and O. Bruhn. A thermodynamic finite-strain model for pseudoelastic shape memory alloys. *Internat. J. Plast.*, 22 (2006) 9:1658–1682.
- [51] B. Peultier, T. Ben Zineb, and E. Patoor, Macroscopic constitutive law for SMA: Application to structure analysis by FEM, *Materials Sci. Engrg. A*, 438-440 (2006) 454–458.
- [52] B. Raniecki and Ch. Lexcellent,  $R_L$  models of pseudoelasticity and their specification for some shape-memory solids, *European J. Mech. A Solids*, 13 (1994) 21–50.
- [53] S. Reese and D. Christ, Finite deformation pseudo-elasticity of shape memory alloys – Constitutive modelling and finite element implementation, *Internat. J. Plast.*, 28 (2008) 455–482.
- [54] T. Roubíček, Models of microstructure evolution in shape memory alloys, in *Nonlinear Homogenization and its Appl. to Composites, Polycrystals and Smart Materials*, P. Ponte Castaneda, J. J. Telega, B. Gambin eds., NATO Sci. Series II/170, Kluwer, Dordrecht, 2004, 269–304.
- [55] A. C. Souza, E. N. Mamiya, and N. Zouain, Three-dimensional model for solids undergoing stress-induced phase transformations, *European J. Mech. A Solids*, 17 (1998) 789–806.
- [56] U. Stefanelli, Magnetic control of magnetic shape-memory single crystals. Submitted, 2011.
- [57] F. Thiebaud, Ch. Lexcellent, M. Collet, and E. Foltete, Implementation of a model taking into account the asymmetry between tension and compression, the temperature effects in a finite element code for shape memory alloys structures calculations, *Comput. Materials Sci.*, 41 (2007) 2:208–221.
- [58] A. Ziolkowski. Three-dimensional phenomenological thermodynamic model of pseudoelasticity of shape memory alloys at finite strains. *Contin. Mech. Thermodyn.*, 19 (2007) 379–398.

DIPARTIMENTO DI MATEMATICA 'F. CASORATI', UNIVERSITÀ DI PAVIA, V. FERRATA 1, I-27100 PAVIA, ITALY

*E-mail address:* `sergio.frigeri@imati.cnr.it`

*URL:* `http://www.imati.cnr.it/sergio`

IMATI - CNR, V. FERRATA 1, I-27100 PAVIA, ITALY AND WIAS, MOHRENSTR. 39, D-10115 BERLIN, GERMANY

*E-mail address:* `ulisse.stefanelli@imati.cnr.it`

*URL:* `http://www.imati.cnr.it/ulisse`